

TECHNICAL DATA

DESCRIPTION: **Deck Mix PM** is single component high slump, polymer modified concrete. **Deck Mix PM** features a dry polymer and special additives for easy placement, finishing, and increased bond strength. Dry polymer gives **Deck Mix PM** excellent bonding characteristics, durability and freeze thaw resistance. In addition, **Deck Mix PM** includes an integral corrosion inhibitor to protect the reinforcing steel. It's easy to use, requiring only the addition of potable water at the jobsite.

USE ON: Tunnels, roads, balconies, parking decks, and elevated structures

- ADVANTAGES:**
- Strip forms one day after placement
 - Pumpable
 - Single component eliminates the need for storage of liquid polymers
 - Requires only the addition of potable water
 - Excellent flexural compressive and bond strength
 - Normal set time with early and continued strength past 28 days
 - Excellent bond to concrete substrates.

	3 DAYS	7 DAYS	28 DAYS
Compressive Strength (ASTM C 39)	3000 psi (20.5 MPa)	4000 psi (27.4 MPa)	6000 psi (41.0 MPa)
Flexural Strength (ASTM C 293)			900 psi (6.2 MPa)
Bond Strength (ASTM C 882 Modified)			2000 psi (13.6 MPa)
Splitting Tensile (ASTM C 496)		700 psi (4.8 MPa)	850 psi (5.8 MPa)

(over)

TECHNICAL DATA

APPLICATION: Add potable water to **Deck Mix PM** at a rate of 3.25 quarts per 80lb bag. Use normal mechanical mixer appropriate for mixing concrete with a coarse aggregate. Mix **Deck Mix PM** with measured water for no more than 3 minutes. Pre-dampen substrate to a surface saturated, dry condition with clean water for a good bond. No special curing is required. Always follow ACI guidelines for application and curing methods. For detail application instructions refer to U.S Concrete Guide Specification Guide.ae

LIMITATIONS: **Deck Mix PM** should be used when ambient temperatures are at 40°F (4°C) and rising. Lower temperatures produce a slower set; higher temperatures produce a faster set. For temperatures below 40°F (4°C) consult with the manufacturer for special cold weather placement provisions which include but are not limited to conditioning of the materials, use of heated mix water and thermal protection. In hot weather use chilled water for mixing. **Deck Mix PM** should not be applied at less than 1" (12.7 mm) thickness.

**PACKAGING/
YIELD:** **Deck Mix PM** is packaged in 80 lb Kraft paper bags. Each bag yields approximately .63 cubic feet when mixed with 3.25 quarts of potable water.

CAUTION: **WARNING! CONTAINS FREE SILICA & PORTLAND CEMENT. DO NOT BREATHE DUST.** May cause delayed lung injury (silicosis). Follow OSHA safety and health standards for crystalline silica (quartz). Cement powder or freshly mixed concrete grout or mortar may cause skin injury. Avoid contact with skin and wash exposed skin areas promptly with water. If any cement powder or mixture gets into the eyes, rinse immediately and repeatedly with water and get prompt medical attention.