

### TECHNICAL DATA

**DESCRIPTION:** **US Thin Patch V/O** is a modified Portland cement based Repair Mortar Mix, containing an integral corrosion inhibitor and dry polymer for added tensile, bond and flexural strengths. **US Thin Patch V/O** is ready to use, requiring only jobsite addition of potable water. Apply in thicknesses from 1/4" to 2" per lift.

**USE ON:** Bridges, tunnels, balconies, parking decks, manholes, sewers, piers, bulkheads, elevated concrete slabs and slabs on grade

- ADVANTAGES:**
- Specially formulated for vertical and overhead repairs
  - Dry polymer provides high bond strength and durability
  - Excellent freeze thaw resistance
  - Very good finishing characteristics
  - Low permeability
  - Economical
  - NSF/ANSI/CAN 61 & 372 certified for drinking water systems

	1 DAY	7 DAYS	28 DAYS
<b>Compressive Strength</b> (ASTM C 109 Modified)	3000 psi (20.68 MPa)	5000 psi (34.47 MPa)	6000 psi (41.37 MPa)
<b>Bond Strength</b> (ASTM C 882 Modified)		1000 psi (6.8 MPa)	2500 psi (17.23 MPa)
<b>Flexural Strength</b> (ASTM C 348)		1200 psi (8.2 MPa)	1800 psi (12.41 MPa)
<b>Freeze Thaw Cycle</b> (ASTM C 666)	99.2% @ 300 cycles		
<b>Length Change</b> (ASTM C 157)	-.031 % (Dry Cured)		
<b>Rapid Chloride Permeability</b> (ASTM C 1202)	<500 Coulombs		
<b>Unit Weight</b>	135 lbs/ft <sup>3</sup>		

### TECHNICAL DATA

**PREPARATION:** Remove all dirt, grease, oil, laitance and curing compounds from concrete, mortar and stone by sandblasting or mechanical roughening. On metals, remove grease, oil, rust and mill scale by sandblasting or wire brushing.

**MIXING:** Pour 100 fluid oz. of water in pail or mortar mixer. In pail, mix with a slow speed drill, while adding 50 lbs. of **US Thin Patch V/O** powder slowly to avoid lumps. (Do not mix more than three minutes). Should small quantities be required, be sure to proportion water accordingly. Masonry surfaces or other absorbent surfaces should be dampened but free of standing water.

**APPLICATION:** Be sure mortar is mixed thoroughly to a uniform consistency. Trowel **US Thin Patch V/O** in prepared area and allow mortar to stiffen, then produce desired finish by using float or rubber gloves, forcing mortar in voids. Apply in thicknesses from 1/4" to 2" per lift. If steel trowel finish is required, wet trowel with water. Protect from wind and heat for the first 24 hours.

If no primer is used, dampen masonry surface to which **US Thin Patch V/O** is applied. On a large project, the use of a good curing compound, meeting ASTM C 309, Type I, will prevent loss of moisture and produce good, durable mortar.

**LIMITATIONS:** **US Thin Patch V/O** should be used when ambient temperatures are 40°F (4°C) and rising. Lower temperatures produce a slower set; higher temperatures produce a faster set. For temperatures below 40°F (4°C) consult with the manufacturer for special cold weather placement provisions which include but are not limited to conditioning of the materials, use of heated mix water and thermal protection. In hot weather use chilled water for mixing.

**PACKAGING:** **US Thin Patch V/O** is packaged in 50 lb multi-wall poly lined bags. This product yield is approximately .42 ft<sup>3</sup>.



Meets the Requirements of  
NSF/ANSI/CAN 61 & 372

Certified to NSF/ANSI/CAN 61  
& 372

NSF/ANSI/CAN 61 & 372

**CAUTION:** **WARNING! CONTAINS FREE SILICA & PORTLAND CEMENT. DO NOT BREATHE DUST.** May cause delayed lung injury (silicosis). Follow OSHA safety and health standards for crystalline silica (quartz). Cement powder or freshly mixed concrete grout or mortar may cause skin injury. Avoid contact with skin and wash exposed skin areas promptly with water. If any cement powder or mixture gets into the eyes, rinse immediately and repeatedly with water and get prompt medical attention.